

**AMENDMENTS TO THE CLAIMS**

1. (Currently Amended) ~~The use of~~ An article comprising three-dimensionally structured surfaces and/or moldings (3D coating) and a coating thereon of melamine resin sheets and/or films produced from cellulosic fiber materials post- or pre- and post-impregnated with an aqueous solution comprising

- (i) a melamine-formaldehyde condensate,
- (ii) an etherified melamine-formaldehyde condensate, and
- (iii) a polymer dispersion.

~~for coating three-dimensionally structured surfaces and/or moldings (3D coating).~~

2. (Currently Amended) The ~~use~~ article as claimed in claim 1, wherein the aqueous solution comprises

- (i) from 5 to 50% by weight of a melamine-formaldehyde condensation product,
- (ii) from 5 to 50% by weight of an etherified melamine-formaldehyde condensate, and
- (iii) from 20 to 90% by weight of a polymer dispersion,

the amounts of components (i), (ii) and (iii) adding up to 100% by weight and being based on the liquid resin mixture.

3. (Currently Amended) The ~~use~~ article as claimed in claim 1 ~~or 2~~, wherein the dispersion (iii) comprises copolymers of acrylates comprising carboxyl, hydroxyl, amide, glycidyl, carbonyl, N-methylol, N-alkoxymethyl, amino and/or hydrazo groups.

4. (Currently Amended) The ~~use~~ article as claimed in ~~any of claims 1 to 3~~ claim 1, wherein the aqueous solution further comprises from 0.1 to 50% by weight of urea based on 100% by weight of the mixture of (i) to (iii).

5. (Currently Amended) The ~~use~~ article as claimed in ~~any of claims 1 to 3~~ claim 1, wherein the aqueous solution comprises

- (i) from 10 to 30% by weight of a melamine-formaldehyde condensation product,

(ii) from 10 to 40% by weight of an etherified melamine-formaldehyde condensation product, and

(iii) from 30 to 80% by weight of a polymer dispersion,

the amounts of components (i), (ii) and (iii) adding up to 100% by weight and being based on the liquid resin mixture.

6. (Currently Amended) The ~~use~~ article as claimed in ~~any of claims 1 to 5~~ claim 1 for coating articles having 3D surfaces and/or sharp-edged elements.

7. (Currently Amended) The ~~use~~ article as claimed in ~~any of claims 1 to 5~~ claim 1 for coating with a single melamine resin sheet and/or film.

8. (Currently Amended) The ~~use~~ article as claimed in ~~any of claims 1 to 5~~ claim 1 for coating woodbase materials.

9. (Currently Amended) The ~~use~~ article as claimed in ~~any of claims 1 to 5~~ claim 1 for coating oriented strand boards (OSB).

10. (Currently Amended) The ~~use~~ article as claimed in claim 1, wherein the cellulosic fiber materials are pre-impregnated with melamine-formaldehyde impregnating resins or with a mixture of melamine-formaldehyde impregnating resins and coating resins or with a mixture of urea-formaldehyde resins and melamine-urea-formaldehyde resins and post-impregnated with said the aqueous solution of (i) to (iii) ~~as set forth in claim 1~~.

11. (Original) A synthetic resin mixture for impregnating cellulosic fiber materials, comprising

(i) from 5 to 50% by weight of a melamine-formaldehyde condensation product,

(ii) from 5 to 50% by weight of an etherified melamine-formaldehyde condensation product, and

- (iii) from 40 to 90% by weight of a copolymer in aqueous dispersion form which is crosslinkable by condensation reaction,  
the amounts of components (i), (ii) and (iii) adding up to 100% by weight and being based on the liquid resin mixture

12. (Original) A synthetic resin mixture as claimed in claim 11, which uses as component (iii) a copolymer of acrylates comprising carboxyl, hydroxyl, amide, glycidyl, carbonyl, N-methylol, N-alkoxymethyl, amino and/or hydrazo groups.

13. (Currently Amended) A melamine resin sheet or film impregnated with a synthetic resin mixture as claimed in claim 11 ~~or 12~~.

14. (Original) A method of 3D coating which comprises applying a melamine resin sheet and/or film as claimed in claim 13 two-dimensionally in one operation to the three-dimensional structure of a material.

15. (Currently Amended) A method of 3D coating which comprises producing melamine resin sheets and/or films from cellulosic fiber materials post- or pre- and post-impregnated with the aqueous solution of ~~any of claims 1 to 3~~ claim 1 and applying them to the three-dimensionally structured surface and/or molding to be coated.

16. (New) The article as claimed in claim 2, wherein the dispersion (iii) comprises copolymers of acrylates comprising carboxyl, hydroxyl, amide, glycidyl, carbonyl, N-methylol, N-alkoxymethyl, amino and/or hydrazo groups.

17. (New) The article as claimed in claim 2, wherein the aqueous solution further comprises from 0.1 to 50% by weight of urea based on 100% by weight of the mixture of (i) to (iii).

18. (New) The article as claimed in claim 3, wherein the aqueous solution further comprises from 0.1 to 50% by weight of urea based on 100% by weight of the mixture of (i) to (iii).

19. (New) The article as claimed in claim 2, wherein the aqueous solution comprises  
(i) from 10 to 30% by weight of a melamine-formaldehyde condensation product,  
(ii) from 10 to 40% by weight of an etherified melamine-formaldehyde condensation product, and  
(iii) from 30 to 80% by weight of a polymer dispersion,  
the amounts of components (i), (ii) and (iii) adding up to 100% by weight and being based on the liquid resin mixture.

20. (New) The article as claimed in claim 3, wherein the aqueous solution comprises  
(i) from 10 to 30% by weight of a melamine-formaldehyde condensation product,  
(ii) from 10 to 40% by weight of an etherified melamine-formaldehyde condensation product, and  
(iii) from 30 to 80% by weight of a polymer dispersion,  
the amounts of components (i), (ii) and (iii) adding up to 100% by weight and being based on the liquid resin mixture.